

The organic vehicle 2002M is designed for fine tuning of automotive silver pastes for backlights. Its solid content allow to maintain viscosity at the desired level and special resins improves adhesion of the dried film.

Shelf life: 8 months @ 4°-10°C, 6 months @ 10-24°C

Typical viscosity 45 – 55 Pa*s

STANDARD TEST CONDITIONS

Viscosity test:

Viscosimeter Brookfield DV II, small sample adapter 6R, spindle 14R, @ 10 r.p.m. and 25 (±0.5) °C